



MARPOL
EMA 6-22
Ethylene-Methyl Acrylate Copolymer



PRODUCT DATA SHEET

PROPERTY	VALUE	ASTM
Melt Index (g/10min)	6.0	D 1238
Methyl Acrylate Content	22%	
Low Temperature Brittleness (C)	-99	D 746
Vicat Softening Point (C)	122	D 1525
Hardness, Shore A	35	D 2240

This information, to our knowledge, is believed to be correct. The use of this product in its actual conditions are beyond our control and satisfactory results for this product is the customer's sole responsibility.