



MARPOL
EVA 1525
Ethylene Vinyl Acetate



PRODUCT DATA SHEET

PROPERTY	VALUE	ASTM
Melt Index 190°C/2.16 kg (g/10min)	25	D 1238
Density (g/cm ³)	0.94	D 792
Vicat Softening Temperature (°F)	131	D 1525
Freezing Point (°F)	145	D 3418
Melting Point (°F)	189	D 3418
Vinyl Acetate Content (%)	15.5	

Description: MARPOL® EVA 1525 is an extrudable ethylene-vinyl acetate copolymer resin available in pellet form for use in conventional extrusion equipment.

Recommended Applications

Heat seal in flexible packaging applications, cast film and adhesive laminates

This information, to our knowledge, is believed to be correct. The use of this product in its actual conditions are beyond our control and satisfactory results for this product is the customer's sole responsibility.



MARCO POLO
INTERNATIONAL, INC.
Worldwide Distributors of Plastic Resins

1121 Walt Whitman Road Suite 301 Melville, NY 11747 Tel: 631-629-4520 Fax: 631-629-4519