




MARPOL
EVA 2825
 Ethylene Vinyl Acetate



PRODUCT DATA SHEET

PROPERTY	VALUE	ASTM
Melt Index (g/10min)	25	D 1238
Density (g/cm ³)	0.952	D 1505
Vinyl Acetate Content (wt %)	27.6	
Tensile Strength at Break (psi)	700	D 638
Elongation at Break (%)	> 800	D 638
Flexural Modulus - 1 % Secant (psi)	2700	D 790
Durometer Hardness, Shore A	70	D 2240
Durometer Hardness, Shore D	19	D 2240
Instrumented Dart Impact (ft-lb)	- 40 °F 19 73 °F 11	D 3763

Recommended Applications

Compounding, hot melt adhesives and masterbatch base resin

Description

MARPOL® EVA 2825 is a high Vinyl Acetate copolymer designed specifically for compounding applications.

This information, to our knowledge, is believed to be correct. The use of this product in its actual conditions are beyond our control and satisfactory results for this product is the customer's sole responsibility.