



**MARPOL**  
**EVA 28800**  
Ethylene Vinyl Acetate



**PRODUCT DATA SHEET**

PROPERTY	VALUE	ASTM
Melt Index (g/10min)	800	D 1238
Density (g/cm <sup>3</sup> )	0.953	D 1505
Vinyl Acetate Content (wt %)	27.6	
Melt Viscosity (MPa)	9300	D 3236
Tensile Strength at Break (psi)	300	D 638
Elongation at Break (%)	360	D 638
Flexural Modulus - 1 % Secant (psi)	2900	D 790
Durometer Hardness, Shore A	69	D 2240
Durometer Hardness, Shore D	18	D 2240

**Recommended Applications**

Adhesives, sealants, industrial sealants, glue sticks, and low viscosity adhesives.

**Description**

MARPOL® EVA 28800 is low viscosity Vinyl Acetate copolymer designed for enhanced tensile performance. This has good compatibility with hydrocarbons, most waxes, and natural tackifiers for making hot melt adhesives, sealants and wax blends.

This information, to our knowledge, is believed to be correct. The use of this product in its actual conditions are beyond our control and satisfactory results for this product is the customer's sole responsibility.