



MARPOL
LL4F 802-SB
Linear Low Density Polyethylene



PRODUCT DATA SHEET

| PROPERTY | VALUE | ASTM |
|-------------------------------------|----------------------|---------|
| Melt Index 190°C/ 2.16kg (g/10 min) | 2.0 | D 1238 |
| Density (g/cm ³) | 0.919 | D 1505 |
| Dart Drop Impact, F50 (grams) | 117 | D 1709A |
| Tensile Strength at Yield (psi) | MD 1800 TD 1500 | D 882 |
| Tensile Strength at Break (psi) | MD 4900 TD 3600 | D 882 |
| 1% Secant Modulus (psi) | MD 32000 TD 36000 | D 638 |

Additives: High Slip and High Antiblock

LL4F 802-SB can - in principle - be used in food contact applications in the USA (FDA) and in Canada (HBP). Migration or use limitations may apply.

This information, to our knowledge, is believed to be correct. The use of this product in its actual conditions are beyond our control and satisfactory results for this product is the customer's sole responsibility.