



**MARPOL**  
**IV 78 HF**  
Polyethylene terephthalate



# PRODUCT DATA SHEET

PROPERTY	VALUE
<b>Intrinsic Viscosity (IV)</b> (dl/g)	<b>.78</b>
<b>Acetaldehyde (AA)</b> (ppm)	<b>&lt; 1.0</b>
<b>Colour 'L'</b> (CIE)	<b>min 82</b>
<b>Colour 'b'</b> (CIE)	<b>0 to -2</b>
<b>Crystallinity</b>	<b>&gt; 50%</b>
<b>Crystalline density</b> (g/cc)	<b>&gt; 1.39</b>
<b>Crystalline Melting Point</b> (C)	<b>255</b>
<b>Moisture (when packed)</b> (w)	<b>&lt; 0.2%</b>
<b>Chips (100 count weight)</b> (g)	<b>1.5</b>
<b>Fines</b> (ppm)	<b>100</b>

This is a food grade PET resin suitable for production of hot-fillable bottles by using heat-setting process during blowing.

This information, to our knowledge, is believed to be correct. The use of this product in its actual conditions are beyond our control and satisfactory results for this product is the customer's sole responsibility.



**MARCO POLO**  
INTERNATIONAL, INC.  
Worldwide Distributors of Plastic Resins

532 Broadhollow Road Suite 104 Melville, NY 11747 Tel: 631-629-4520 Fax: 631-629-4519