



**MARPOL**  
**IV 84 CB**  
Copolymer PET



# PRODUCT DATA SHEET

PROPERTY		VALUE	TEST
Intrinsic Viscosity (IV)	(dl/g)	.84	QAF-PCL-3.414
Acetaldehyde (AA)	(ppm)	1.0	QAF-PCL-3.413
Colour 'b'	(CIE)	0 to -3	QAF-PCL-3.211
Crystallinity		50%	QAF-PCL-3.415
Chips /g		72	QAF-PCL-3.408
Fines	(ppm)	100	QAF-PCL-3.407

#### Features:

- Good process ability
- Excellent clarity/gloss
- Very Good mechanicals

#### It is typically used for:

- Carbonated drinks.
- Agro chemicals
- APET sheet and PET strapping

#### Certifications:

PET MarPol IV 84 CB resin is considered safe for food-packaging applications based on compliance with FDA regulation 21 CFR Section 177.1630 & other similar food contact safety regulations.

This information, to our knowledge, is believed to be correct. The use of this product in its actual conditions are beyond our control and satisfactory results for this product is the customer's sole responsibility.



**MARCO POLO**  
INTERNATIONAL, INC.  
Worldwide Distributors of Plastic Resins

532 Broadhollow Road Suite 104 Melville, NY 11747 Tel: 631-629-4520 Fax: 631-629-4519