



**MARPOL**

**LL8F 801**

Linear Low Density Polyethylene Octene



# PRODUCT DATA SHEET

Property	Value	ASTM
Melt index 190°C/ 2.16kg (g/10 min)	1.0	D 1238
Density (g/cm <sup>3</sup> )	0.919	D 1505
Dart Drop Impact (grams) F50	250-380	D 1709A
Tensile Strength (psi)		D 882
MD	1800	
TD	1500	
Tear Strength (grams)		D 1922
MD	4900	
TD	3600	
1% Secant Modulus (psi)		D 882
MD	25000	
TD	28000	

**Additives:** No Slip, No Antiblock

These suggestions and data are based on information we believe to be reliable. They are offered in good faith, but without guarantee as conditions and methods of use are beyond our control. We recommend that the prospective user determine the suitability of our materials and suggestions before adopting them on a commercial scale.